



# Calc500

## Physical Properties

Brightness	93 %
CaCO <sub>3</sub>	90%
Specific Gravity	2.50
Tapped Bulk Density	1.30
Oil Absorption g/100g	14-20 ML
D-98	25.0 μ
D-50	7.9 μ
Appearance	Free Flowing Dry Powder
Retention on 400 #	0.10% MAX
Loss on Heating	0.10 % At 105 ± 2° C / 3Hrs
Water Demand Test	35-45 ML / 100 GM

## Particle Size Analysis

