



Dolo20M

Physical Properties

Brightness	93 %
Specific Gravity	2.62
Tapped Bulk Density	0.30
Oil Absorption g/100g	14-20 ML
D-98	20.0 μ
D-50	5.0 μ
Appearance	Free Flowing Dry Powder
Retention on 400 #	0.10% MAX
Loss on Heating	0.30 % At 105 ± 2° C / 3Hrs
Water Demand Test	35-45 ML / 100 GM

Particle Size Analysis

